



## PEC (multi-coloured) Recycled Polyester geotextile fabrics

Physical Properties	test method	unit															Tolerance	
<b>Weight</b>		<b>g/m<sup>2</sup></b>	<b>150</b>	<b>200</b>	<b>250</b>	<b>300</b>	<b>350</b>	<b>400</b>	<b>500</b>	<b>600</b>	<b>700</b>	<b>800</b>	<b>1000</b>	<b>1200</b>	<b>1500</b>	<b>±</b>	<b>10%</b>	
<b>Thickness</b>	EN ISO 9863-1	mm	1.00	1.20	1.40	1.60	1.80	2.00	2.30	2.60	2.90	3.30	4.00	4.50	6.40	±	20%	
<b>Mechanical Properties</b>																		
<b>Tensile Strength</b>	<b>md</b>	EN ISO 10319	kN/m	1.0	1.6	2.0	2.4	2.8	3.2	4.0	5.4	6.7	8.0	10.0	12.0	15.0	-	10%
	<b>cmd</b>	EN ISO 10319	kN/m	1.0	1.6	2.1	2.5	3.0	3.4	5.0	7.4	9.0	10.5	13.5	15.0	20.0	-	10%
<b>Elongation at max load</b>	<b>md</b>	EN ISO 10319	%	50	50	50	50	50	50	60	60	70	70	80	80	90	±	30%
	<b>cmd</b>	EN ISO 10319	%	60	60	60	60	60	60	60	60	70	70	80	80	90	±	30%
<b>Energy index</b>	EN ISO 10318	kJ/m <sup>2</sup>	0.3	0.4	0.6	0.7	0.8	0.9	1.4	1.9	2.7	3.2	4.7	5.4	7.9	±	20%	
<b>Static puncture resistance</b>	EN ISO 12236	kN	0.2	0.3	0.4	0.5	0.6	0.8	1.2	1.8	2.2	2.6	4.2	5.0	6.0	-	10%	
<b>Dynamic puncture resistance (cone drop test)</b>	EN ISO 13433	mm	>50	46	40	36	32	24	14	10	8	6	2	2	0	+	20%	
<b>Pyramid puncture resistance</b>	EN 14574	N	n/a	200	300	400	450	500	600	800	950	1100	1500	1700	2000	-	20%	
<b>Hydraulic properties</b>																		
<b>Permeability normal to the plane</b>	EN ISO 11058	mm/s	90	90	70	60	60	50	30	30	25	20	10	10	10	-	30%	
<b>In-plane flow capacity</b>	EN ISO 12958	10 <sup>-3</sup> /ms	2	2	2	3	3	3.2	5	7	7	8	9	9	9	-	30%	
<b>Opening size</b>	EN ISO 12956	µm	65	60	55	55	55	45	45	35	35	35	30	30	20	±	30%	
<b>Durability properties</b>																		
<b>Weathering resistance</b>	EN 12224	Passes EN 12224 weathering test. It is highly recommended that the geotextile is covered within 15 days from the day of installation. The material can be exposed to sunlight with a degradation of the mechanical properties depending on season.																
		Made from multicoloured polyester recycled fibre. Specific weight of polymer is 0.38 kg/dm <sup>3</sup> . Raw material is staple fibres, produced through needlepunching and calendering. The material is produced according the quality management system of EN ISO 9001:2008. It fulfills the requirement of European regulations related to construction products as per 1213-CPR 3269.																
<b>Oxydation resistance</b>	EN ISO 13438	Forecast minimum durability of 5 years for every application in natural grounds with 4<pH<9 and soil temperature <25°C																

The values given are an average obtained in our laboratories and in official testing insitutes

The confidence level is 95%

We reserve the right to make changes at any time without notice



Wallbarn Ltd • Unit 16 Capital Business Centre, 22 Carlton Road, South Croydon, Surrey, CR2 0BS, UK



Notified body



1213-CPD-3269